



ARMORFLO 200

HIGH PERFORMING SMOOTHENING SELF-LEVELLING UNDERLAYMENT

PRODUCT DESCRIPTION

ARMORFLO 200 is a self-smoothing underlayment for medium to heavy duty industrial flooring applications such as warehouse, factory and industrial floors requiring durability and strength. It is designed for easy application on concrete floors over concrete floors as an underlayment for subsequent placement of floor coverings.

FEATURES AND BENEFITS

- Aesthetically nice self-leveling and smooth finish
- Fast setting, can be worked on within 3 to 4 hours, depending on the temperature
- Excellent workability, can be poured or pumped
- Minimal shrinkage and outstanding resistance to crack
- Excellent bond strength

APPLICATION AREAS

ARMORFLO 200 can be used for smoothing underlayment of the following areas:

- Industrial floor and warehouse
- Self-leveling of interior and exterior areas before floor coverings
- Leveling of wood subfloors

SURFACE PREPARATION

Prepare concrete substrate in accordance with International Concrete Repair Institute (ICRI) Technical Guideline. Remove all unsound concrete and provide a profiled, porous surface. Substrate must be structurally sound, dust-free, and free of grease, oil, dirt, curing compounds, release agents, or any other surface or penetrated contaminants that will adversely affect bond. Pressure wash the surface with a commercial pressure washer (3000 psi, 4 GPM) (21MPa, 0.25 L/s) and allow to fully dry before application.

PRIMING: Apply one coat of ARMORLATEX acrylic primer to allow for good bonding and adhesive purpose, for a very porous concrete surface ensure that two coat of primer is applied to ensure surface is well saturated with the primer before application.

APPLICATION INSTRUCTION

MIXING: Pour 5 Litres of water into a clean plastic or metal bucket, pour ARMORFLO 200 into the clean bucket of water, then mix with a power mixer at 400 RPM for two minutes.





ARMORFLO 200

HIGH PERFORMING SMOOTHENING SELF-LEVELLING UNDERLAYMENT

APPLICATION AND INSTALLATION

Pour the material on the area to be resurfaced using a smoothing trowel ,because of the self-leveling property of ARMORFLO 200 the material can easily be finished as desired, spike roller will be used to eliminate entrapped air or bubbles and to give a uniform appearance. The level of thickness will also be determined by the application need, but should be achieved in one application; the mixed material can be applied at a thickness between 3mm and 20 mm. If the mix hardens, it should be disposed, please do not attempt to remix or add water to hardened mix.

SPECIFICATION

ARMORFLO 200 should be specified for factory floors, warehouses, hospital setc and underlayment for floor coverings. It is particularly suitable for areas requiring hardwearing and durable flooring.

TECHNICAL DATA

PROPERTIES	TYPICAL RESULT	TEST METHOD
Compressive Strength 1 day	20mpa	EN-13892- 2
Compressive Strength 7 days	25mpa	
Compressive Strength 28 days	35mpa	
Flexural Strength 1 day	3.45mpa	EN-13892- 2
Flexural strength 28days	6.9mpa	
Drying time	24 hours	ASTMC 191
Light traffic and application	24hours	
Application thickness	3mm – 10mm	

CLEANING AND HEALTH

Remove the excess mortar on tools with copious amount of water; if already dry you can remove through mechanical means. Also prolonged contact with skin may occur as it is the case with all cementitious based material, therefore safety gloves and glasses should be used when working.

PACKAGING AND SELF LIFE

ARMORFLO 200 is packed in 20 kg and 25kg bags .Store in a cold dry place. With proper storage material can be stored and used within 12 month

LIMITED WARRANTY

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice

