

ARMORFLO-500HD

**TWO COMPONENT, SOLVENT FREE EPOXY
FLOOR PRIMER FOR CONCRETE**

PRODUCT DESCRIPTION

ARMORFLO-500HD is Two-component epoxy based primer with high solid content for epoxy flooring. It is employed as first coat and intermediate coat.

FEATURES AND BENEFITS

- High chemical and physical resistance
- Excellent compressive strength
- Excellent flexural and tensile strength
- Seamless dust free and easy to clean.
- Dense corrosion resistant surface

APPLICATION AREAS

ARMORFLO-500HD can be applied as a primer and basecoat coat over metal and concrete surfaces in:

- factories
- warehouses
- Shopping centers
- workshops
- aircraft hangars
- Schools and hospitals
- Pharmaceutical and food industries
- laboratories
- car parks
- waste water treatment plants
- areas where heavy forklifts and corrosive chemicals are of concern

APPLICATION INSTRUCTION

Surface preparation:

New concrete and plaster must be allowed to cure for at least 28 days

Weak, cracked, broken sections in the concrete floor must be repaired using Filling Compound and Grout Repair Compounds; loose and unstable floors must be reinforced with anchorage after multilayer lamination.

Mixing process:

Mix the whole two components together. You should prepare all mixtures in a mechanical way using low speed (300-400 rpm) electric mixer. Avoid stirring more than necessary in order to minimize entrapped air inside the mixture.

APPLICATION CONDITION

Surface Temperature:

Minimum +10°C / Maximum +30°C

Ambient Temperature:

Minimum +10°C / Maximum +30°C

Material Temperature:

It must be between +10°C and +30°C.

Surface Moisture Content:

Humidity rate in the concrete must be maximum 4%.

Relative Humidity:

It must be maximum 80%.

Dew Point:

Temperature of the surface to be applied must be at least 30°C above the dew point.



ARMORFLO-500HD

TWO COMPONENT, SOLVENT FREE EPOXY FLOOR PRIMER FOR CONCRETE

SPECIFICATION

- Number of Components :** 2
- Thinner for Application :** Not Available
- Gloss :** Glossy
- Mixture Pot Life :** 40 Minutes /23°C 200g.
(DIN 16945)
- Mode of application:** Paint Roller, Brush
- Consumption:** 400 g/cm² (200-225 μ dry film thickness), depending on the surface.
- VOC :** 0 g/l (does not contain volatile organic materials.)
- Package :** 11.25 kg + 3.75 kg
- Shelf Life :** 1 year in its original intact container at temperatures between +5 and + 25°C

TECHNICAL DATA

DRYING TIME			
Temperature	Pedestrian Traffic	Mechanical Strength	Chemical Resistance
+10°C	36 hours	5 days	10 days
+ 20°C	24 hours	3 days	7 days
+30°C	16 hours	2 days	5 days

SHELF LIFE

1 year in its original intact container at temperatures between +5 and + 25°C.

SAFETY PRECAUTIONS

- R - (Risk phrases)
- R36/37/38- Irritating to eyes, respiratory system and skin.
 - R42/43- May cause sensitization by inhalation and skin contact.
 - R51/53- Toxic to aquatic organisms, may cause long-term adverse effects in the aquatic environment.

- S – (Safety phrases)
- S26- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
 - S36/37/39- Wear suitable protective clothing, gloves and eye/face protection.

S46- If swallowed, seek medical advice immediately and show this container or label.

Health and safety instructions available in the materials safety data sheet (MSDS) should be observed. Adequate ventilation must be provided during application. Wear protective equipments such as mask and gloves. Avoid direct touch and do not inhale vapors ... Keep away from heat, hot surfaces, sparks, open flames and other ignition sources.





ARMORFLO-500HD

**TWO COMPONENT, SOLVENT FREE EPOXY
FLOOR PRIMER FOR CONCRETE**

LIMITED WARRANTY

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice

