



# ARMORKRYSTAL 600 PLUS

## 4TH GENERATION CRYSTALLINE INTEGRAL WATERPROOFING ADMIXTURE

WATERPROOFING ADMIXTURE

### PRODUCT DESCRIPTION

**ARMOKRYSTAL 600 PLUS** - is a 4th generation powder crystalline Integral waterproofing admixture designed to resist hydrostatic pressure and for all concrete requiring primary waterproofing. The innovative crystalline technology within ARMOKRYSTAL 600 PLUS reacts with moisture silicate and free lime, a natural by-product of the cement hydration process. This 4th generation crystalline is not only hydrophilic but has hydrophobic properties as well.

The reaction creates millions of Nano-crystals which grow throughout the concrete pores and capillary tract. Thus, the concrete becomes permanently sealed against the penetration of water or liquids from any direction. The concrete is protected from the deterioration due to harsh environmental conditions.

**ARMOKRYSTAL 600 PLUS** has been specifically formulated to meet the different temperature and climate conditions.

### TYPICAL APPLICATIONS

**ARMOKRYSYAL 600 PLUS** can be used for the structural waterproofing of all concrete structures such as:

- Reservoirs
- Sewage and Water Treatment Plants
- Foundation and retaining Wall
- Underground Vaults
- Secondary Containment Structures
- Tunnels and Subway Systems
- Swimming Pool
- Concrete Slabs and Precast panels

### ADVANTAGES / BENEFITS

- Extremely resistant to hydrostatic pressure from both negative and positive side of the slab
- Increases freeze thaw resistance of the concrete
- Becomes an integral part of the concrete.
- Highly resistant to aggressive chemicals and protect reinforcement against corrosion.
- Non-toxic (NSF 61 certified for potable water applications)
- Negligible effect on slump, air entrainment, plasticizers and water reducers.
- Permeability tested as per ACE (Army corps of Engineers)
- Allows concrete to breathe and can seal hairline crack up to 0.4mm

### DIRECTION FOR USE

**Dosage Rate:** 0.8-1% by weight of cement. Consult with ARMORSIL's Technical Department for assistance in verifying the appropriate dosage rate and for further information regarding enhanced chemical resistance and optimum concrete performance for your project. it should be added to the mixing water

**Mixing:** ARMOKRYSTAL 600 PLUS must be added to the concrete at the time of batching.





# ARMORKRYSTAL 600 PLUS

## 4TH GENERATION CRYSTALLINE INTEGRAL WATERPROOFING ADMIXTURE

WATERPROOFING ADMIXTURE

### SETTING TIME AND STRENGTH

The setting time of concrete is affected by the chemical and physical composition of ingredients, temperature of the concrete and climatic conditions. ARMORKRYSTAL 600 PLUS will have little or no effect on the set time. However, concrete with ARMORKRYSTAL 600 PLUS may deliver higher compressive strength than normal concrete

### SPECIFICATION

**ARMORKRYSTAL 600 PLUS** should be specified for all concrete surfaces subject to hydrostatic pressure or water attack.

**ARMORKRYSTAL 600 PLUS** meets ACI 212 classification of Permeability Reducing Admixture for Hydrostatic Condition (**PRAH**)

### TECHNICAL INFORMATION

Resistance to hydrostatic pressure at 16 bar	No leakage DIN 1048 Pt.5
Depth of water penetration	38mm
Co-efficient of Permeability reduction%	93% DIN 1048 Pt 5
Chloride content	NIL
Color	Grey
Density	1.350 g/cm <sup>3</sup>

### PACKAGING AND SHELF

**ARMORKRYSTAL 600 PLUS** are packed in 20kg buckets. Store in a cold dry place. With proper storage material, can be stored and used within 12 months

### CLEANING AND HEALTH

**ARMORKRYSTAL 600 PLUS** is a non-hazardous material, however because it is used with Portland cement it should be known prolonged contact with skin by Portland cement may lead to irritation, as it is the case with all cementitious based material, therefore safety gloves and glasses should be used when working with cement.

### LIMITED WARRANTY

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice

